

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (currently amended): A biodegradable composition comprising:
between 40 and 85% by weight of poly(lactic acid),
~~between 10 and 40% by weight of poly(epsilon-caprolactone)~~between 0.1 and 10% by
weight of co-polyester polymer with adipic acid, and
between 5 and 10% by weight magnesium silicate,
each on the basis of the total weight of the biodegradable composition.

Claim 2 (previously presented): The biodegradable composition according to claim 1, said composition comprising at least magnesium and silicon.

Claim 3 (previously presented): The biodegradable composition according to claim 1, to which composition during its preparation less than 5% of an organic peroxide, on the basis of the total weight of the final biodegradable composition, has been added.

Claim 4 (previously presented): The biodegradable composition according to claim 3, to which composition during its preparation less than 2% of an organic peroxide, on the basis of the total weight of the final biodegradable composition, has been added.

Claim 5 (previously presented): The biodegradable composition according to claim 4, to which composition during its preparation less between 0.1 to 1.8% of an organic peroxide, on the basis of the total weight of the final biodegradable composition, has been added.

Claim 6 (previously presented): The biodegradable composition according to claim 3, wherein said organic peroxide is selected from the group consisting of diacetyl peroxide, cumyl-hydro-peroxide, dibenzoyl peroxide, 2,5-dimethyl-2,5-di(terbutylperoxy)-hexane, and mixtures thereof.

Claim 7 (currently amended): The biodegradable composition according to claim 1, ~~said composition further comprising a~~ wherein the co-polyester polymer with adipic acid is present in an amount of less than 5% by weight on the basis of the total weight of the composition.

Claim 8-10 (cancelled)

Claim 11 (currently amended): A film or coating comprising a biodegradable composition, said biodegradable composition comprising:

between 40 and 85% by weight of poly(lactic acid),

between 10 and 40% by weight of poly(epsilon caprolactone), and

between 5 and 10% by weight of magnesium silicate, and

less than 5% by weight of an organic peroxide, wherein said organic peroxide is added to a mixture of said poly(lactic acid) and poly(epsilon caprolactone),

each on the basis of the total weight of the biodegradable composition.

Claim 12 (previously presented): The film or coating according to claim 11, wherein said film or coating is on an article comprising a material selected from the group consisting of paper, plastics, wood and composite materials.

Claim 13 (previously presented): The film or coating according to claim 11, to which composition during the preparation less than 5% of an organic peroxide, on the basis of the total weight of the final biodegradable composition, has been added.

Claim 14 (previously presented): The film or coating according to claim 11, to which composition during its preparation less than 2% of an organic peroxide, on the basis of the total weight of the final biodegradable composition, has been added.

Claim 15 (previously presented): The film or coating according to claim 11, to which composition during its preparation less between 0.1 to 1.8% of an organic peroxide, on the basis of the total weight of the final biodegradable composition.

Claim 16 (original): The film or coating according to claim 15, wherein said organic peroxide is selected from the group consisting of diacetyl peroxide, cumyl hydro peroxide, and dibenzoyl peroxide.

Claim 17 (previously presented): The film or coating according to claim 11, said biodegradable composition further comprising a co-polyester polymer with adipic acid in an amount of less than 5% by weight on the basis of the total weight of the composition.

Claim 18 (previously presented): The film or coating according to claim 11, said biodegradable composition further comprising at least two of the elements selected from the group consisting of magnesium, aluminum, and silicon.

Claim 19 (original): The film or coating according to claim 11, said composition further comprising plasticizers.

Claim 20 (currently amended): The film or coating according to claim ~~13~~11, said composition further comprising up to 5% of a mono-ester, on the basis of the total weight of the biodegradable composition.

Claim 21 (currently amended): A molded or formed article comprising a biodegradable composition, which biodegradable composition comprises between 40 and 85% by weight of poly(lactic acid), ~~between 10 and 40% by weight of poly(epsilon caprolactone)~~between 0.1 and 10% by weight of co-polyester polymer with adipic acid, and between 5 and 10% by weight of magnesium silicate, each on the basis of the total weight of the biodegradable composition.

Claim 22 (previously presented): A molded or formed article according to claim 21, wherein said molded or formed article is selected from the group consisting of utensils, table service-ware forks, spoons, knives, chopsticks, containers, cups, foam material products, and pots.

Claim 23 (currently amended): An article comprising a section made of a material selected from the group consisting of paper, plastics, wood and composite materials, said section being coated with a coating or a film, said coating or film comprising between 40 and 85% by weight of poly(lactic acid), between 10 and 40% by weight of poly(epsilon caprolactone), and between 5 and 10% by weight of magnesium silicate each on the basis of the total weight of the ~~biodegradable composition~~coating or film, wherein less than 5% by weight of an organic peroxide is added to a mixture of said poly(lactic acid) and poly(epsilon caprolactone) on the basis of the total weight of the coating or film.

Claim 24 (currently amended): An article of claim ~~25~~23, said article being selected from the group consisting of food service-ware, plates, cups, packaging, cardboard boxes, and trays.

Claim 25 (currently amended): A method of producing an article comprising a biodegradable composition, comprising the steps of:

providing a biodegradable composition, said composition comprising
between 40 and 85% by weight of poly(lactic acid),
between 10 and 40% by weight of poly(epsilon caprolactone), and
between 5 and 10% by weight of mineral particles, comprising magnesium silicate, each
on the basis of the total weight of the biodegradable composition, wherein less than 5% by
weight of an organic peroxide is added to a mixture of poly(lactic acid) and poly(epsilon
caprolactone) on the basis of the total weight of the final biodegradable composition; and
preparing a film or coating from said composition.

Claim 26 (currently amended): A method of producing a biodegradable composition, comprising the steps of:

(i) providing a composition comprising between 40 and 85% by weight of poly(lactic acid), ~~and between 10 and 40% by weight of poly(epsilon caprolactone)~~ between 0.1 and 10% by weight of co-polyester polymer with adipic acid, and between 5 and 10% by weight of mineral particles, comprising magnesium silicate, each on the basis of the total weight of the biodegradable composition, which method comprises the following steps:

- (ii) mixing the constituents of (i);
- (iii) heating the mixture to a temperature 160°C to 210°C; and
- (iv) forming the resultant mixture to obtain a desired shape.

Claim 27 (previously presented): The method of claim 25 including the step of applying said film or coating on an article comprising a material selected from the group consisting of paper, plastics, wood and composite materials.

Claim 28 (new): The coating or film according to Claim 11, wherein the biodegradable composition further comprises between 10 and 40% by weight of poly(epsilon caprolactone).

Claim 29 (new): The article according to Claim 21, wherein the biodegradable composition further comprises between 10 and 40% by weight of poly(epsilon caprolactone).

Claim 30 (new): The method according to Claim 26, wherein the biodegradable composition further comprises between 10 and 40% by weight of poly(epsilon caprolactone).